



The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd  
NO.205 Jiangtian RD(E).,Songjiang  
Shanghai China  
Postal Code: 201613  
Tel:(021)57747878  
Fax:(021)51685279  
Website: <https://www.escort.com.cn/CN>

## TEST REPORT

MATERIAL : EP 70 DURO WHITE

COMPOUND NO: E7001W

| Physical Properties (Press Cure:170°CX10min Post Cure:150°CX1h) | Requirement | Test result |
|-----------------------------------------------------------------|-------------|-------------|
| Hardness,Point 硬度(邵A)                                           | 65.00~75.00 | 73.00       |
| Tensile Strength,min,Mpa 拉力強度                                   | 8.00        | 8.10        |
| Ultimate Elongation,min,% 延伸率                                   | 200.00      | 403.00      |
| Specific Gravity, 比重                                            |             | 1.38        |
| Heat Resistance 70h@100°C 老化試驗                                  |             |             |
| Change in hardness,max,Point 硬度變化(邵A)                           | ±15.00      | +3.00       |
| Change in tensile strength,max,% 拉伸強度變化率                        | ±30.00      | -12.00      |
| Change in ultimate elongation,max,% 扯斷伸長率變化率                    | -50.00      | -25.00      |
| Compression Set 22h@70°C 壓縮永久變形試驗                               |             |             |
| Compression set,Method B,max,% 壓縮永久變形                           | 25.00       | 11.00       |

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY  
THIS COMPOUND E7001W CAN MEET ASTM 2000 M8BA708A14B13

