The Manufacturer of Sealing Parts

Escort Seal (Shanghai) Co., Ltd
NO.205 Jiangtian RD(E).,Songjiang
Shanghai China
Postal Code: 201613
Tel:(021)57747878
Fax:(021)51685279
Website: https://www.escort.com.cn/CN

# TEST REPORT

MATERIAL : AFLAS 70 DURO BLACK COMPOUND NO: L7001B

| Physical Properties (Press Cure:170℃X10min Post Cure:200℃X16h) | Requirement | Test result |
|---|---|---|
| Hardness,Point 硬度(邵A) | 65.00~75.00 | 75.00 |
| Tensile Strength,min,Mpa 拉力強度 | 14.00 | 19.50 |
| Ultimate Elongation,min,% 延伸率 | 175.00 | 238.00 |
| Specific Gravity, 比重 | | 1.57 |
| **Heat Resistance 70h@250℃ 老化試驗** | | |
| Change in hardness,max,Point 硬度變化(邵A) | +10.00 | -3.00 |
| Change in tensile strength,max,% 拉伸強度變化率 | -25.00 | -15.00 |
| Change in ultimate elongation,max,% 扯斷伸長率變化率 | -25.00 | +20.00 |
| **Compression Set 22h@200℃ 壓縮永久變形試驗** | | |
| Compression set,Method B,max,% 壓縮永久變形 | 50.00 | 28.00 |

NOTE: THE ABOVE TESTS WAS TESTED WITH TEST PIECE AND FOR YOUR REFERENCE ONLY

THIS COMPOUND L7001B CAN MEET ASTM 2000 M2HK714A1-10B38




**QA Manager:** Dabou Ku **QC.Dept:** LingLing.Li **Test by:** QC08